

KETJENFLEX® 9S

Reactive Plasticizer

AXC.04.06

General Information

KETJENFLEX® 9S is a toluene sulfonamide based reactive plasticizer used in Melamine laminates, Coatings and Adhesives.

Description and Application

KETJENFLEX® 9S is a basic starting material in the preparation of melamine formaldehyde based resins for laminates. KETJENFLEX® 9S imparts post formability, improved gloss, impact resistance, reduced shrinkage and warp of the hardened laminate.

KETJENFLEX® 9S can be used in high and low pressure melamine formaldehyde laminates, urea formaldehyde resins and as reactive plasticizer in epoxy and polyurethane based resins. In addition, systems reacted with KETJENFLEX® 9S show improved resistance to oils, solvents and moisture. KETJENFLEX® 9S has good thermal stability.

Applications include:

- Melamine formaldehyde resins for laminates
- Melamine/urea formaldehyde wood adhesives
- Phenol formaldehyde wood adhesives
- Melamine based coatings
- Epoxy adducts
- Polyurethane coating and adhesives
- Raw material for fluorescent pigments
- Brightening agent for metal plating

Specifications

Active content:	≥ 99.0%
Water content:	≤ 0.3%
Ortho content:	35-45%
Colour *):	≤ 30 Pt/Co

*) 30% in acetone

Physical Properties

Appearance:	White crystalline powder
Melting point:	112°C
AHEW:	171
Degrades at:	187°C
Apparent bulk density:	650-850 kg/m ³
Flash point (open cup):	180°C

Toxicological information

Acute toxicity (oral):	LD50, rat ≥ 2000 mg/kg
Genotoxicity (Amestest):	not mutagenic
Biodegradation:	readily biodegradable

KETJENFLEX® 9S is approved by the U.S. Food and Drug Administration (FDA) according to CFR 21, section:

- 175.105

Packaging

- 25 kg in 3 ply paper bags, 35 on a pallet

Storage

Keep packaging well closed. Store in a cool dry place.

Think about your impact on the environment: reduce, reuse or recycle! Contact Axcentive if you feel we could be of help.

The information presented herein is true and accurate to the best of our knowledge, but without any guarantee unless explicitly given. Since the conditions of use are beyond our control, we disclaim any liability, including for patent infringement, incurred in connection with the use of these products, data or suggestions.

KETJENFLEX® is a registered trademark of Axcentive SARL

Europe, Americas, Middle East and Africa
Axcentive SARL
Chemin de Champouse
13320 Bouc Bel Air, France
Phone: +33 4 42 69 40 90
E-mail: info@axcentive.com
Web: www.axcentive.com

Asia, India and Australasia
Axcentive Asia Pte Ltd
13 Lorong 8 Toa Payoh, #07-01 Braddell Tech Park
319261 Singapore
Phone: +65 6258 6338
E-mail: info@axcentive.com
Web: www.axcentive.com